



PRODUCT DATASHEET

Protective treatment - Coatings

Minatol Cira Matt

Protective treatment with silky matt finish and excellent tread safety - added resistance against certain types of hand disinfectant





Minatol Cira Matt



pH value (Concentrate): 7–8

Important ingredients:

Polymers, Waxes, Solvents, Surfactants,
Preservatives, Colourant

Recommended dosage:



Protective treatment
Undiluted

METHODS
finder



APPLICATION

- The protective treatment with satin finish
- For treating hard and elastic floor coverings (PVC, linoleum, natural and artificial stone, etc.)
- High tread safety

PROPERTIES

- Polymer/wax-based
- Matt to satin finish
- Water vapour diffusion guaranteed
- Forms a polishable, water-resistant protective film
- Added resistance against ACO-derm V and AHD 2000 (alcohol-based hand disinfectants)

PLEASE NOTE

- Shake well before use
- Not suitable for water and damp-sensitive floor coverings (e.g. anhydrite), for outdoor areas and wet zones
- Treat porous floor coverings with Porosol before use
- Not suitable for plastic floors with a grained surface
- Apply at a temperature of 15-25°C and 30-70% relative humidity
- Before each use, make sure that the floor covering is pH-neutral

RECOMMENDED APPLICATION METHOD

Coating (protective treatment)

The floor covering must be clean, free of any earlier treatment and completely dry (<3% residual moisture, CM method). Dry vacuum/mop the floor covering to collect dust. Apply the protective coating in sections in 2 to 3 thin coatings. Allow the floor to dry well between coats (at least 60 minutes). Where required, polish with a polishing pad once fully dry (after 2 to 3 days).

STORAGE

Store in original container at 15 to 25°C and protected from sunlight. Keep container closed when not in use. Protect against frost.

Durability (unopened): 24 Month

Wetrol AG shall have no liability whatsoever for damage caused by incorrect use. Observe special cleaning and care instructions from the floor covering manufacturer.